



MADE IN CANADA


We believe in better.

Heartland Polymers' portfolio of quality polypropylene is produced at North America's first single-site PDH/PP facility, located in Alberta, Canada with access to all major hubs and ports. Sustainability is built into our very design, and we are committed to providing customers with responsibly produced polymer. We are ready to provide a high quality, reliable source of polypropylene to help you and your customers meet your goals where you need it, when you need it. At Heartland Polymers, we believe in better: People. Polymer. Performance. Planet. Made in Canada, serving the world, we produce polypropylene that makes a difference for you and for your customers.

CONNECT WITH HEARTLAND POLYMERS

150 John F. Kennedy Parkway, Suite 401
Short Hills, New Jersey 07078

ppsales@heartlandpolymers.com

 @HeartlandPP

HeartlandPolymers.com

 Heartland Polymers

Quality resins produced sustainably, delivered reliably

All of our polypropylene features the following attributes:

- Excellent balance of processability and physical properties
- A tailored balance of stiffness to impact properties
- Exceptional heat and chemicals resistance
- Excellent price to performance ratio
- Lower density translating into weight savings
- Recyclable
- Phthalate free
- Free of any Animal Derived Materials (ADM)
- Meets the FDA requirements for direct and indirect food contact

Discover the Heartland difference

We offer three different grades of polypropylene for BOPP, cast film and TWQ. With our film polypropylene grades, you can expect:

- Enhanced draw down
- High speed processability
- High clarity



FABRICATION FAMILY			FILM HOMOPOLYMERS		FILM RANDOM CO-POLYMERS
GRADE NAME			H3003	H3209	R3208
PRIMARY APPLICATION			BOPP	Cast film	Cast film
PROPERTIES	UNITS	TEST METHOD	NOMINAL VALUES		
Melt Flow Rate (2.16 kg at 230°C)	g/10 min	ASTM D1238	3.0	8.8	8.0
Tensile Strength @ Yield 50 mm/min (2 in/min)	MPa (psi)	ASTM D638	33 (4,800)	35 (5,000)	25 (3,650)
Tensile Elongation @ Yield	%	ASTM D638	12	11	14
Flexural Modulus 1% Secant 1.3 mm /min (0.05 in/min)	MPa (psi)	ASTM D790	1,375 (200,000)	1,300 (190,000)	760 (110,000)
Notched Izod Impact Strength @ 23°C	J/m (ft-lb/in.)	ASTM D256A	32 (0.6)	27 (0.5)	58 (1.1)
Heat Deflection Temperature (HDT) @ 0.45 MPa/ (66 psi)	°C (°F)	ASTM D648	95 (203)	93 (199)	73 (163)
MAIN FEATURE			High speed	High clarity	High clarity
APPLICATION DETAILS			High speed BOPP metallizable film	Stationary, sheet protectors, photo albums, DVD case covers, packaging	Mono and multilayer cast films or multilayer blown films for packaging, retort pouches, shrink and stretch wrap

Suffix Legend: A = Anti-static; B = Anti-block; E = Nucleation/mold release; G = Anti-gas fading; H = Heat stabilized; N = Nucleated/clarified; S = Slip/mold release; U = UV stabilizer; Z = Others